



**Johns Manville**

**World Headquarters**

Johns Manville  
717 17th Street  
Denver, CO 80202 • USA  
Phone: + 1 (303) 978-2000  
[www.im.com](http://www.im.com)

**DuraSpun®**  
Polyester Spunbond  
**T 011/270**



**0991**  
**02**  
**0991-CPD-0001**

**Johns Manville GmbH, Wupperstrasse 10, D-14167 Berlin**

**EN 13249:2000-12 + EN 13249/A1:2005-01**  
**EN 13251:2000-12 + EN 13251/A1:2005-01**  
**EN 13253:2000-12 + EN 13253/A1:2005-01**  
**EN 13255:2000-12 + EN 13255/A1:2005-01**  
**EN 13257:2000-12 + EN 13257/A1:2005-01**

**EN 13250:2000-12 + EN 13250/A1:2005-01**  
**EN 13252:2000-12 + EN 13252/A1:2005-01**  
**EN 13254:2000-12 + EN 13254/A1:2005-01**  
**EN 13256:2000-12 + EN 13256/A1:2005-01**  
**EN 13265:2000-12 + EN 13265/A1:2005-01**

Geotextiles used for Filtration (F), Reinforcement (R) and Separation (S) in the construction of roads and other traffic areas, railways (excl. asphalt inclusion), in earthworks, foundations and retaining structures, in drainage systems, in erosion control works (coastal protection, bank revetments), in the construction of reservoirs, dams and canals, in solid waste disposals and in liquid waste containment projects.

**Technical Product Data**

Test criterion	Test norm	Unit	Mean value	Tolerance
Max. tensile strength/MD	EN ISO 10319	[kN/m]	19.2	- 1.9
Max. tensile strength /CD	EN ISO 10319	[kN/m]	15.0	- 1.5
Elongation at max. tensile strength/MD	EN ISO 10319	[%]	60	± 12
Elongation at max. tensile strength/CD	EN ISO 10319	[%]	70	± 14
Hole size cone drop test	EN ISO 13433	[mm]	18	+ 2
CBR	EN ISO 12236	[kN]	3.0	- 0.3
Opening size	EN ISO 12956	[µm]	100	± 20
Water permeability	EN ISO 11058	[10 <sup>-3</sup> m/s]	3.0	- 0.9

**Durability:**

- to be covered within 30 days after installation
- durable for a minimum of 25 years for applications without reinforcement function in natural soils with 4 <pH <9 and soil temperature <25°C.

**CONTACTS :**

**EUROPE**

Johns Manville Sales GmbH  
Max-Fischer-Strasse 11  
86399 Bobingen • Germany  
Phone: +49 (0) 8234/9670-553 Waterpr.  
Phone: +49 (0) 8234/9670-561 Filtr.+Sep.  
Fax: +49 (0) 8234/9670-588

Johns Manville Sales GmbH  
Werner-Schuller-Strasse 1  
97877 Wertheim • Germany  
Phone: +49 (0) 9342/801-281 Con.+Ind.  
Phone: +49 (0) 9342/801-130 Flooring  
Fax: +49 (0) 9342/801-491

**USA**

Johns Manville  
995 MT. Pleasant Road  
Spartanburg, SC 29307 • USA  
Phone: +1-864-579-8215  
Fax: +1-864-579-8275

**ASIA**

JM Shanghai Nonwovens Co., Ltd.  
No. 153 Huaying Road  
Qingpu, Shanghai 201700 • PR China  
Phone: +86 (0) 21 59720007  
Fax: +86 (0) 21 59728116

Status: January 2011 (3rd version, replaces 2nd version of January 2008)